

IABCO ENi3 SAW

SAW wire for low alloy steels

Product name	IABCO ENi3 SAW
Classification EN ISO	14171-A: S2Ni3
Material No.	-
Classification AWS	A5.23: ENi3
Approvals	TÜV 12686.00, CE.
Applications	Submerged arc welding of fine grain structural steel where high impact values are required.
Base materials	For cryogenic construction steels and Ni bearing low temperature steels. ASTM: A203 grades D/E/F, A333/A334 grades 3/7, A350 grade LF3/LF5, A352 grade LC3. 12Ni14.
Typical analysis of wire, weight %	C: 0.09 Si: 0.17 Mn: 1.05 Ni: 3.20
Typical heat treatment ⁽¹⁾	Preheat and PWHT are often not necessary but actual requirements will depend on the grade and thickness of material being welded and any design codes that apply.
Mechanical properties of weld deposit ⁽²⁾	Mechanical properties will be dependent on the welding procedure and flux.
Other products	TIG/GTAW: ENi3.

Notes (1) Application codes and project specifications should always be referred to for specific requirements.

(2) Actual mechanical properties will be dependent on specific welding procedure (including shielding gas, flux, PWHT etc) and should always be confirmed by approval of an appropriate welding procedure.