

IABCO EQ316L

Stainless steel strip for strip cladding

Product name	IABCO EQ316L
Classification EN ISO	14343-A: B 19 12 3 L
Material No.	-
Classification AWS	A5.9: EQ316L
Approvals	-
Applications	A 316L austenitic stainless steel strip used for cladding with both the electroslag and sub-arc processes. Most commonly used as a 60mm wide by 0.5mm thick strip. EQ316L will normally be used in combination with EQ309L or EQ309LMo strip in a two, or three, layer procedure to produce a final 316L analysis deposit. Typical applications include cladding large vessels used in the petrochemical, refinery and chemical industries.
Base materials	Suitable for cladding most pressure vessel and boiler steels. Typical steels to be clad will include CMn, CrMo and CrMoV.
Typical analysis of wire, weight %	C: 0.01 Si: 0.40 Mn: 1.9 Cr: 18.3 Ni: 12.7 Mo: 2.9
Typical heat treatment ⁽¹⁾	Actual welding procedure (including preheat and interpass temperature) will depend on the base material that is being clad.
Mechanical properties of weld deposit ⁽²⁾	-
Other products	Strip: IABCO EQ309L, IABCO EQ309LMo, IABCO EQ309LNb, IABCO EQ347. Flux: UNISCO 1944 (electroslag).

Notes (1) Application codes and project specifications should always be referred to for specific requirements.

(2) Actual mechanical properties will be dependent on specific welding procedure (including shielding gas, flux, PWHT etc) and should always be confirmed by approval of an appropriate welding procedure.